

Appl. No. 09/754,264
Amendment and/or Response
Reply to Office Action of November 19, 2004

Page 3 of 8

Amendments to the Claims:

A clean version of the entire set of pending claims (including amendments to the claims, if any) is submitted herewith per 37 CFR 1.121(c) (3). This listing of claims will replace all prior versions, and listings, of claims in the application.

Listing of Claims:

10. (Previously Presented) A method of depositing a wiring thin film over a semiconductor substrate, the method comprising:

providing a Al_3Ti target;

providing a substrate;

forming a Ti layer over said substrate;

sputter depositing an Al_3Ti layer on said Ti layer using said Al_3Ti target;

and annealing said substrate at a temperature of at least 400 °C to promote absorption of Si into said Al_3Ti layer.

11. (Previously Presented) A method as recited in claim 10, wherein an Al layer is deposited on said Al_3Ti layer.

12. (Previously Presented) A method as recited in claim 10, further comprising pattern-etching said Al layer thereby forming a wiring pattern.

13. (Previously Presented) A method as recited in claim 10, wherein the method further comprises forming an insulating layer between said substrate and said Al_3Ti layer.

Atty. Docket No. OKI.202

Appl. No. 09/754,264
Amendment and/or Response
Reply to Office Action of November 19, 2004

Page 4 of 8

14. (Currently Amended) A method of forming a wiring film, the method comprising:
providing a substrate;
depositing a Ti layer over said substrate;
depositing an Al-Si-Cu layer on said Ti layer, which forms an Al₃Ti on
said Ti layer; and
pattern etching an Al layer, which forms beneath said Al-Si-Cu layer;
and
after the depositing of the Al-Si-Cu layer, annealing the substrate at a temperature of
at least 400 °C.
15. (Previously Presented) A method as recited in claim 14, wherein said Al-Si-Cu
layer is deposited at a temperature of at least 400 °C.
16. (Cancelled)
17. (Previously Presented) A method of forming a wiring film, the method
comprising:
providing a substrate;
depositing an Al₃Ti layer over said substrate;
depositing an Al layer on said Al₃Ti layer; and
pattern etching said Al layer; and
after the depositing of the Al layer, annealing the substrate at a temperature of at
least 400 °C.
18. (Previously Presented) A method as recited in claim 17, wherein said Al layer is
deposited at a temperature of at least 400 °C.
19. (Cancelled)

Atty. Docket No. OKI.202

Appl. No. 09/754,264
Amendment and/or Response
Reply to Office Action of November 19, 2004

Page 5 of 8

20. (Previously Presented) A method as recited in claim 17, wherein said Al_3Ti layer is deposited at a temperature of at least 400 °C.

Atty. Docket No. OKI.202